PLYMOUTH TUBE CO USA
601 Grantham Avenue
West Monroe, LA 71292
(318) 388 - 3360

Heat: 560415 PO: 4510291261 Date 04/01/2021

Sold To:
Webco Industries, Inc.
P. O. BOX 100
SAND SPRINGS, OK 74063

Customer's Order No. 10070534 **Date:** 03-22-21

Invoice Number:

Page 1 of 1

Mill Order Number: 192155-1-1

TEST REPORT

TR# 192155

Size: 0.7500" OD X 0.0830" MIN. WALL
Grade: TPS31803/S32205 SEAMLESS
Specifications: ASTM A789(20)/ASME SA789(19) STAINLESS PRESSURE TUBING
Finish tubes solution bright annealed at a minimum temperature of 1925°F and rapidly cooled in an inert atmosphere.

Heat	Lot Numbers	Yield Strength lbs per sq. in.	Tensile Strength lbs per sq. in.	% Elong in 2"	Hardness Test	
560415	1	98300 / 102200	127500 / 127800	34.00 / 34.00	RC 22-24	2 Tests

Test	Status	Comments
Flare	OK	
Eddy Current	OK	ASTM A-1016 100%

Heat	C	MN	P	S	SI	CR	NI	MO	CU	CO	N
560415											
Ladle	0.013	0.810	0.023	0.001	0.520	22.340	5.180	3.110	0.140	0.055	0.181
Product	0.013	0.810	0.025	0.001	0.530	22.310	5.280	3.130	0.150	0.057	0.180

Additional Requirements:
165 STRAIGTHT TUBES PRODUCED PER WEBCO INDUSTRIES, INC. PO. 10070534. MATERIAL COMPLIES WITH EN10204 3.1. TUBES MANUFACTURED IN THE USA. COUNTRY OF MELT: SWEDEN.

We hereby certify this report to be correct. **By** Clariel Thomas – APPROVED Q.A.-TECHNICAL

Plymouth Tube Company